

DATA SHEET

ALLOY 201 | 2.4068

Major specifications

UNS N02201 | ASTM B162

Product forms

Coils and Sheets

The current Stock Range can be found on www.sd-metals.com. Further dimensions available upon request.

Key features

Commercially pure Nickel (Alloy 201), with good mechanical properties and excellent corrosion resistance in many environments. Compared to nickel alloys, Nickel 201 has high electrical and thermal conductivity and good magnetostrictive properties. It also maintains high ductility over a wide range of temperatures.

Areas of application

Electrical and electronic components, electrode contacts, anodes, battery plates, fuel cells and electroplating components.

CHARACTERISTIC

Chemical composition limits in %	Physical constants and thermal properties	Typical mechanical properties (room temperature)
C max. 0,02	Density 8,89 g/cm ³	Yield strength min. 103 MPa
Ni (+Co) min. 99,00	Melting point 1435 - 1446 °C	Tensile strength min. 403 MPa
	Thermal conductivity 79 W/m • °C	Elongation min. 50 %
	Electrical resistivity 0,085 µohm•m	
	Coefficient of expansion at 21-93°C 13,1 µm/m • °C	

All information is subject to change without notice.
The properties correspond to the material in the heading. They may vary for other specifications. Please contact us for more details.

Do you have any questions? Contact us:

Julius Mönkeberg

+49 4174 66 94 -118

j.moenkeberg@sd-metals.com

Jacob Schmidt

+49 4174 66 94 -217

j.schmidt@sd-metals.com